

THE ORIGINAL DIRECT/INDIRECT® PHOTOSTENCIL SYSTEM

The quality of film with the durability of emulsion.

DIRECT/INDIRECT® PHOTOSTENCIL SYSTEM

- Accurate, predictable stencil thickness control for difficult repeat jobs.
- Excellent print quality.
- Excellent durability for long print runs.
- For use with solvent-based, UV and plastisol inks.

The Direct/Indirect System is a two-part system that combines the print quality of film with the durability of emulsion. Ideal for documented quality systems requiring minimal process variance.



Direct/Indirect films are not pre-sensitized and will not age on the shelf. D-2 Diazo Transfer Emulsion contains a unique, very high sensitizer ratio essential to properly sensitize the film for imaging and maximum durability

MATERIALS REQUIRED

Exposure unit
Washout sink
Clean work area
40-50 durometer soft rounded squeegee

RECOMMENDED

Drying cabinet
Pressure washer

CHEMICALS REQUIRED

Chroma/Clean™ mesh degreaser
Chroma/Strip™ screen reclaimer

RECOMMENDED

Chroma/Set™ screen blockout

SAFETY AND HANDLING

There are no hazards associated with this product when used within reasonable standards of industrial hygiene and safe working practices. Refer to SDS for further information.

STORAGE

Unsensitized Direct/Indirect films should be stored in a closed container in a cool, dry area.

Sensitized D-2 Emulsion has a shelf life of 4-6 weeks and should be refrigerated between using.

Protect from freezing. D-2 emulsion is not freeze/thaw stable.

SIZE/THICKNESS	MESH COUNT	APPLICATION
D-50 (0.5 mil/13μ)	280 - 420	Fine halftones, detailed line art and UV inks.
D-75 (0.75 mil/19μ)	230 - 330	Fine halftones and UV printing.
A-100 (1.0 mil/25μ)	140 - 280	General purpose printing, medium ink deposit, light blue for easy registration.
B-100 (1.0 mil/25μ)	140 - 280	General purpose printing, halftones plus medium ink deposit.
B-150 (1.5 mil/38μ)	150 & coarser	For opaque and heavy ink laydown; ideal for solder mask.
B-200 (2.0 mil/50μ)	150 & coarser	For heaviest deposit. Used most often for textile, some graphic applications.

DIRECT/INDIRECT FILM


DIRECT/INDIRECT[®] PHOTOSTENCIL SYSTEM



INSTRUCTIONS

PREPARE

Add water to sensitizer and mix solution into D-2 Transfer Emulsion. Place the film, emulsion side up, on a clean, flat surface which is smaller than the inside dimensions of the screen frame. Place screen, squeegee side up, on film.




COAT

Pour a bead of transfer emulsion at one end of screen. With light squeegee pressure, coat emulsion across screen with soft, roundedged (40-50 durometer) squeegee. Card off excess emulsion. The coated screen should have a shiny or wet look. If not, relood and squeegee again.



DWELL STEP

After coating with transfer emulsion, allow time for the emulsion to sensitize the film. Chromaline recommends 5 - 15 minutes for this dwell step. Do not use heat or fan. NOTE: The thicker the stencil, the longer the dwell step should take.



DRY

After dwell step is complete, dry screen in a dark area at a temperature no higher than 110° F. Screen is not dry if the clear backing is difficult to remove. Screen will be dry in approximately 30 minutes.

EXPOSE

To expose, remove the clear backing and place the emulsion side of the positive against the print side of the screen in an exposure frame. Refer to exposure chart.



RECLAIM

To develop, gently spray both sides of the screen with warm water. Wait approximately 30 seconds, then wash the print side of the screen until the image is fully open and foaming has stopped. Rinse squeegee side and dry completely. You are now ready to print.



EXPOSURE GUIDELINES

Note: Exposure times are suggested only as a guide. Use step exposure method or an exposure calculator to determine optimal exposure times. Individual exposure times may vary depending upon equipment used, bulb age, and other shop conditions.

UV EXPOSURE CHART

Starting exposure times for Direct/Indirect Emulsion System using D2 Transfer Emulsion and a 230 yellow polyester monofilament mesh. Chromaline recommends the use of an exposure calculator or step exposure for determining your best exposures with your equipment and conditions.

Film	1KW @ 18"	5KW @ 40"
D-50	3 min. 15 sec.	2 min. 00 sec.
D-75	3 min. 45 sec.	2 min. 30 sec.
A-100	3 min. 45 sec.	2 min. 30 sec.
B-100	4 min. 00 sec.	2 min. 45 sec.
B-150	4 min. 30 sec.	3 min. 15 sec.
B-200	5 min. 15 sec.	4 min. 00 sec.

Film Roll Size	Transfer Emulsion
26" x 50'	One Quart
26" x 200'	One Gallon
52" x 50'	Two Quarts
52" x 200'	Two Gallons

* Exposure times were determined using the Chromaline UV Minder Radiometer/Dosimeter and CHROMALINE EXPOSURE CALCULATOR.

For Technical Service
Call Toll Free **1-800-328-4261**
(Outside North America Call **+1-218-628-2217**)
Email: **help@chromaline.com**